

Roof Product List

List Current as of August 1, 2008

*As of December 31, 2007, all new ENERGY STAR qualified products are prohibited from being cleaned during testing.

**Warranty does not necessarily cover solar reflectance.

Company Name	Brand	Model	Type	Initial Solar Reflectance	Solar Reflectance after 3 years	Initial Emissivity	Low Slope?	Steep Slope?	Roof Cleaned Prior to 3rd Year Test*	Warranty (Years)**
Abolin Co.	Cool Barrier	Facade White	Coating	0.89	0.85	0.90	Y	Y	No	5
Abolin Co.	Cool Barrier	O10	Coating	0.43	0.42	0.89	N	Y	No	5
Abolin Co.	Cool Barrier	O11	Coating	0.64	0.61	0.88	N	Y	No	5
Abolin Co.	Cool Barrier	O12	Coating	0.70	0.66	0.88	Y	Y	No	5
Abolin Co.	Cool Barrier	O13	Coating	0.82	0.77	0.86	Y	Y	No	5
Abolin Co.	Cool Barrier	O14	Coating	0.83	0.79	0.86	Y	Y	No	5
Abolin Co.	Cool Barrier	O15	Coating	0.84	0.80	0.87	Y	Y	No	5
Abolin Co.	Cool Barrier	O16	Coating	0.79	0.75	0.87	Y	Y	No	5
Abolin Co.	Cool Barrier	O17	Coating	0.66	0.60	0.86	Y	Y	No	5
Abolin Co.	Cool Barrier	O18	Coating	0.39	0.35	0.89	N	Y	No	5
Abolin Co.	Cool Barrier	O19	Coating	0.86	0.83	0.88	N	Y	No	5
Abolin Co.	Cool Barrier	O20	Coating	0.80	0.78	0.89	Y	Y	No	5
Abolin Co.	Cool Barrier	O21	Coating	0.77	0.74	0.89	Y	Y	No	5
Abolin Co.	Cool Barrier	O22	Coating	0.74	0.70	0.89	Y	Y	No	5
Abolin Co.	Cool Barrier	O23	Coating	0.60	0.55	0.89	N	Y	No	5
Abolin Co.	Cool Barrier	O24	Coating	0.29	0.29	0.91	N	Y	No	5
Abolin Co.	Cool Barrier	O25	Coating	0.70	0.68	0.90	Y	Y	No	5
Abolin Co.	Cool Barrier	OO1	Coating	0.73	0.71	0.87	Y	Y	No	5
Abolin Co.	Cool Barrier	OO2	Coating	0.84	0.82	0.86	Y	Y	No	5
Abolin Co.	Cool Barrier	OO3	Coating	0.87	0.85	0.88	Y	Y	No	5
Abolin Co.	Cool Barrier	OO4	Coating	0.45	0.43	0.90	N	Y	No	5
Abolin Co.	Cool Barrier	OO5	Coating	0.75	0.68	0.87	Y	Y	No	5
Abolin Co.	Cool Barrier	OO6	Coating	0.76	0.71	0.86	Y	Y	No	5
Abolin Co.	Cool Barrier	OO7	Coating	0.42	0.41	0.89	N	Y	No	5
Abolin Co.	Cool Barrier	OO8	Coating	0.62	0.60	0.89	N	Y	No	5
Abolin Co.	Cool Barrier	OO9	Coating	0.74	0.70	0.87	N	Y	No	5
Abolin Co.	Cool Barrier	Roof White	Coating	0.89	0.83	0.89	Y	Y	No	5
AcryLabs	AcryLabs	2100	Coating	0.86	0.74	0.90	Y	Y	Yes	10
Acrylux Paint Manufacturing Co. Inc.	Acrylux	Roof Flat	Coating	0.87	0.74	0.90	Y	Y	No	5
Acrylux Paint Manufacturing Co. Inc.	Acrylux	Roof Gloss	Coating	0.91	0.76	0.90	Y	Y	No	5
Acrylux Paint Manufacturing Co. Inc.	Acrylux	Roof Mastic	Coating	0.87	0.66	0.89	Y	Y	No	5
Acrylux Paint Manufacturing Co. Inc.	Acrylux	Super Roof Mastic	Coating	0.86	0.72	0.89	Y	Y	No	5
Acrymax Technologies, Inc.	Acrymax	AF-130	Coating	0.85	0.75	0.90	Y	Y		5 - 10
Adurel International Inc.	Adurel	A808	Coating	0.84	0.66	0.88	Y	Y	No	5
Adurel International Inc.	Adurel	MS2200	Coating	0.80	0.73	0.88	Y	Y	No	5
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Flex	Coating	0.89	0.85	0.89	Y	Y		10
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Flex: Urethane	Coating	0.88	0.84	0.88	Y	Y		10
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Flex: Ceramic	Coating	0.88	0.84	0.89	Y	Y		10
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Flex: Hydro	Coating	0.91	0.87	0.88	Y	Y		10
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Flex: Sub Zero	Coating	0.90	0.83	0.89	Y	Y		10
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Kool	Coating	0.88	0.82	0.88	Y	Y		10
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Shield	Coating	0.88	0.84	0.89	Y	Y		10
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Shield: Ceramic	Coating	0.89	0.82	0.89	Y	Y		10
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Shield: F.R.C.	Coating	0.86	0.82	0.88	Y	Y		10
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Shield: Sub Zero	Coating	0.88	0.84	0.89	Y	Y		10
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Shield: Urethane	Coating	0.88	0.84	0.88	Y	Y		10
Advanced Coating Systems, Inc.	Kool-Roof	Kool-Roof	Coating	0.89	0.82	0.89	Y	Y	No	10
Akzo Nobel Coatings	CERAM-A-STAR 1050	KH	Coating	0.55	0.55	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	821-35W018-511	Coating	0.47	0.46	0.86	N	Y	No	10
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XA3G41335	Coating	0.39	0.38	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XA3Y41357	Coating	0.39	0.38	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XA3Y41601	Coating	0.30	0.30	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XA5G41220	Coating	0.37	0.35	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XG3G40889	Coating	0.29	0.28	0.86	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XG3G41345	Coating	0.28	0.28	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XG3Y42033	Coating	0.34	0.34	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3G40855	Coating	0.54	0.51	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3G40861	Coating	0.50	0.48	0.88	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3G41211	Coating	0.52	0.51	0.87	N	Y	No	40

Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3G41213	Coating	0.60	0.58	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3G41216	Coating	0.33	0.32	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3G41332	Coating	0.52	0.52	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3G41893	Coating	0.58	0.60	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3G41894	Coating	0.51	0.51	0.88	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3Y41142A	Coating	0.48	0.46	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3Y41371	Coating	0.48	0.47	0.86	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3Y41600	Coating	0.55	0.50	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3Y41653	Coating	0.28	0.29	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XL3Y41136A	Coating	0.26	0.26	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XR3G40857	Coating	0.35	0.42	0.88	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XR3G40864	Coating	0.30	0.33	0.86	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XR3G41331	Coating	0.32	0.32	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XR3G41711	Coating	0.35	0.35	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XR3G41881	Coating	0.35	0.35	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XR3Y41364	Coating	0.30	0.30	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XR3Y41366	Coating	0.32	0.32	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XR3Y42037	Coating	0.32	0.32	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XR5G41223	Coating	0.32	0.32	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XT3G41215	Coating	0.36	0.36	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XW3G40863	Coating	0.58	0.54	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XW3G41212	Coating	0.65	0.63	0.87	Y	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XW3G41214	Coating	0.56	0.46	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XW3G41328	Coating	0.57	0.54	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XW3G41885	Coating	0.61	0.61	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XW3Y41356	Coating	0.51	0.52	0.88	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XW3Y41374	Coating	0.58	0.54	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XW3Y42034	Coating	0.57	0.54	0.87	N	Y	No	40
Akzo Nobel Coatings	CERAM-A-STAR® 900	SA3X33318	Coating	0.35	0.35	0.88	N	Y	No	25
Akzo Nobel Coatings	CERAM-A-STAR® 900	SH3X30570	Coating	0.59	0.57	0.87	N	Y	No	25
Akzo Nobel Coatings	CERAM-A-STAR® 900	SH3X31581	Coating	0.51	0.49	0.87	N	Y	No	25
Akzo Nobel Coatings	CERAM-A-STAR® 900	SL3X32940 Harbor Blue	Coating	0.32	0.32	0.87	N	Y	No	25
Akzo Nobel Coatings	CERAM-A-STAR® 900	ST3X30571	Coating	0.36	0.37	0.87	N	Y	No	25
Akzo Nobel Coatings	CERAM-A-STAR® 900	SW3X24009	Coating	0.55	0.46	0.87	N	Y	No	20
Akzo Nobel Coatings	CERAM-A-STAR® 900	SW3X31091	Coating	0.64	0.60	0.86	N	Y	No	25
Akzo Nobel Coatings	CERAM-A-STAR® 900	SW3X32695	Coating	0.60	0.60	0.86	N	Y	No	25
Akzo Nobel Coatings	CERAM-A-STAR® 940	SR3P24003	Coating	0.41	0.41	0.87	N	Y	No	25
Akzo Nobel Coatings	CERAM-A-STAR® 940	SR3P24003 Crimson Red	Coating	0.39	0.39	0.87	N	Y	No	25
Akzo Nobel Coatings	CERAM-A-STAR® 940	SR3P32680	Coating	0.40	0.40	0.87	N	Y	No	25
Akzo Nobel Coatings	CERAM-A-STAR® 940	SR5P24847 Red	Coating	0.31	0.31	0.86	N	Y	No	20
Akzo Nobel Coatings	CERAM-A-STAR® 950	828-30W018-214 Light Gray	Coating	0.27	0.28	0.87	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	828-30W018-98 White	Coating	0.62	0.51	0.87	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	828-35A018-116 Light Blue	Coating	0.26	0.26	0.88	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	828-35D018-221A Sandstone	Coating	0.57	0.45	0.87	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	828-35G018-23 Light Green	Coating	0.44	0.46	0.86	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	828-35R018-29 Red	Coating	0.30	0.30	0.86	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	828-35W018-219A Shasta White	Coating	0.67	0.58	0.87	Y	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	828-75W018-220A Classic White	Coating	0.66	0.54	0.87	Y	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	SA3G23796 Ash Gray	Coating	0.39	0.38	0.87	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	SA3G24195 Old Town Gray	Coating	0.27	0.28	0.87	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	SA5G24008	Coating	0.37	0.35	0.87	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	SD3G23791 Sand Gold	Coating	0.53	0.52	0.87	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	SG3G23794 Colony Green	Coating	0.34	0.34	0.87	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	SG3G23799	Coating	0.35	0.37	0.88	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	SG3G24471 Aspen Green	Coating	0.30	0.30	0.86	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	SG3G24638 Patina Green	Coating	0.27	0.27	0.87	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	SG3G32684 Marine Green	Coating	0.38	0.38	0.87	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	SH3G23793 Light Stone	Coating	0.52	0.51	0.88	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	SL3G24499 Dresden Blue	Coating	0.25	0.23	0.87	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	SR3G23792 Rustic Red	Coating	0.30	0.30	0.87	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	ST3G23790 Sahara Tan	Coating	0.36	0.36	0.86	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	ST3G23798 Desert Beige	Coating	0.32	0.32	0.86	N	Y	No	30
Akzo Nobel Coatings	CERAM-A-STAR® 950	SW3G23789 Polar White	Coating	0.57	0.54	0.87	N	Y	No	30

Akzo Nobel Coatings	CERAM-A-STAR® 950	SW3Y39701	Coating	0.75	0.73	0.86	Y	Y		30
Akzo Nobel Coatings	CERAM-A-STAR® 950U	SW3K86249	Coating	0.57	0.58	0.84	N	Y	No	30
Akzo Nobel Coatings	POLYDURE® 1000	PW3R14874	Coating	0.52	0.51	0.86	N	Y	No	10
Akzo Nobel Coatings	POLYDURE® 1000	PW3R16675	Coating	0.57	0.59	0.88	N	Y	No	10
Akzo Nobel Coatings	POLYDURE® 1000	PW3R17090	Coating	0.57	0.59	0.88	N	Y	No	10
Akzo Nobel Coatings	POLYDURE® 1000	PW5R23596	Coating	0.61	0.61	0.87	N	Y	No	10
Akzo Nobel Coatings	POLYDURE® 1000	PW5R28944	Coating	0.61	0.61	0.87	N	Y	No	10
Akzo Nobel Coatings	POLYDURE® 500	PA3R28304	Coating	0.34	0.36	0.88	N	Y	No	10
Akzo Nobel Coatings	POLYDURE® 500	PH3N25430	Coating	0.47	0.49	0.88	N	Y	No	10
Akzo Nobel Coatings	POLYDURE® 500	PW3R27331	Coating	0.54	0.56	0.88	N	Y	No	10
Akzo Nobel Coatings	Polyester	PT3R22548	Coating	0.33	0.35	0.87	N	Y	No	10
Akzo Nobel Coatings	Polyester	PW3R14238 White	Coating	0.56	0.51	0.86	N	Y	No	10
Akzo Nobel Coatings	Polyester	PW3R28421A	Coating	0.53	0.56	0.87	N	Y	No	10
Akzo Nobel Coatings	TRINAR®	KA3R16482 Silver	Coating	0.29	0.30	0.87	N	Y	No	30
Akzo Nobel Coatings	TRINAR®	KA3R23092 Ash Gray	Coating	0.38	0.38	0.87	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KA3R32732	Coating	0.38	0.39	0.87	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KA3R34130	Coating	0.38	0.39	0.87	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KA3R83013	Coating	0.37	0.38	0.87	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KD3R16489	Coating	0.47	0.48	0.85	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KD3R23115 Aztec Gold	Coating	0.46	0.46	0.86	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KG3R32729	Coating	0.29	0.30	0.87	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KG3R34133	Coating	0.41	0.41	0.87	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KH3R17370	Coating	0.38	0.40	0.87	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KH3R17371	Coating	0.57	0.54	0.85	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KH3R24309 Ivory	Coating	0.54	0.49	0.86	N	Y	No	30
Akzo Nobel Coatings	TRINAR®	KH3R27112	Coating	0.28	0.28	0.85	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KL3R21873	Coating	0.30	0.30	0.88	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KM2R34129	Coating	0.41	0.41	0.86	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KM2R34922	Coating	0.50	0.51	0.86	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KM3R32736	Coating	0.37	0.37	0.86	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KR0R29171	Coating	0.32	0.32	0.88	N	Y	No	30
Akzo Nobel Coatings	TRINAR®	KR3R25386	Coating	0.33	0.33	0.88	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KR3R32720	Coating	0.49	0.49	0.87	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KR3R34128	Coating	0.38	0.40	0.87	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KR3R42714	Coating	0.40	0.39	0.87	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KR3R86913	Coating	0.37	0.38	0.87	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KR3Y41059	Coating	0.26	0.26	0.87	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KT3R16484	Coating	0.41	0.42	0.87	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KT3R19238 Sahara Tan	Coating	0.43	0.42	0.87	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KT3R21713	Coating	0.39	0.39	0.87	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KT3R25385 Surfsand	Coating	0.33	0.34	0.86	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KW3R17374 Bone White	Coating	0.70	0.69	0.85	Y	Y	No	35
Akzo Nobel Coatings	TRINAR®	KW3R18399 Morton White	Coating	0.56	0.52	0.85	N	Y	No	30
Akzo Nobel Coatings	TRINAR®	KW3R19235 Polar White	Coating	0.59	0.57	0.86	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KW3R21584	Coating	0.56	0.57	0.88	N	Y	No	40
Akzo Nobel Coatings	TRINAR®	KW3R31524 Morton White	Coating	0.55	0.53	0.86	N	Y	No	30
Akzo Nobel Coatings	TRINAR®	KW3R32718	Coating	0.67	0.69	0.87	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KW3R37513	Coating	0.56	0.52	0.87	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KW3R83034	Coating	0.62	0.57	0.87	N	Y	No	35
Akzo Nobel Coatings	TRINAR®	KWIR36036	Coating	0.71	0.71	0.87	Y	Y	No	35
All Weather Surfaces Hawaii	Acry-Chem	White	Coating	0.83	0.73	0.88	Y	N	No	20
All Weather Surfaces Hawaii	Hawaiin Sun Guard	White	Coating	0.83	0.75	0.88	Y	N	No	5-20
All Weather Surfaces Hawaii	Solar Gard	White	Coating	0.83	0.73	0.88	Y	N	No	20
All Weather Surfaces Hawaii	Tropical Roof Shield	White	Coating	0.83	0.75	0.88	Y	N	No	5-20
All-White Roofs & Manufacturing, Inc.	All White	R400	Coating	0.90	0.75	0.89	N	Y	No	3
American Hydrotech Inc	Cool-Cap	M-100 White Coat	Coating	0.86	0.70	0.94	Y	N	No	5 - 10
American Rooftile Coatings	Rooftile Paint - ARC	Terra Cotta M-3308	Coating	0.36	0.23	0.85	N	Y	No	10
American Rooftile Coatings	White Roof Mastic Coating	M4100	Coating	0.84	0.72	0.86	Y	N	No	10
American Weatherstar	Weatherstar Coatings	Acrylic 210	Coating	0.81	0.64	0.90	Y	Y	Yes	10
American Weatherstar	Weatherstar Coatings	Acrylic 211	Coating	0.85	0.57	0.89	Y	Y	No	5-15
Andek Corporation	Andek	Polaroof AC	Coating	0.83	0.55	0.94	Y	Y		10
Andek Corporation	Andek	Polaroof NW	Coating	0.81	0.52	0.93	Y	Y	No	10
ARC	PLSI	DynaSHIELD Flashing Grade	Coating	0.79	0.73	0.95	Y	Y	No	5
ARC	PLSI	DynaSHIELD Seam Sealer	Coating	0.80	0.73	0.95	Y	Y	No	5
ARC	PLSI	DynaSHIELD White Coating	Coating	0.82	0.61	0.95	Y	Y	No	5
ARC	PLSI	DynaSHIELD White Coating	Coating	0.82	0.59	0.95	Y	Y	No	5

ARC	PLSI	HydroSHIELD Insulating Ceramic Roof Coat	Coating	0.80	0.79	0.96	Y	Y	No	10
ARC	PLSI	HydroSHIELD Standard White	Coating	0.80	0.66	0.96	Y	Y	No	5
ARC	PLSI	Hydrotherm Petro Coat	Coating	0.80	0.77	0.93	Y	Y	No	5
ARC	PLSI	Hydrotherm Roof Coat/Paint	Coating	0.80	0.65	0.96	Y	Y	No	10
ARC	PLSI	SEBS White Coating	Coating	0.82	0.61	0.95	Y	Y	No	5
ARC	PLSI	SEBS White Flashing Cement	Coating	0.79	0.73	0.95	Y	Y	No	10
BASF Corporation	Fluoroceram	815G105 Hemlock Green	Coating	0.29	0.31	0.84	N	Y	Yes	35
BASF Corporation	Fluoroceram	815G34 Patina Green	Coating	0.32	0.34	0.85	N	Y	Yes	35
BASF Corporation	Fluoroceram	815R1 Terra Cotta	Coating	0.31	0.32	0.82	N	Y	Yes	35
BASF Corporation	Fluoroceram	815W32 Shasta White	Coating	0.54	0.54	0.85	N	Y	Yes	35
BASF Corporation	Fluoroceram	815W42 Parchment	Coating	0.46	0.49	0.85	N	Y	Yes	35
BASF Corporation	Fluoroceram	815W49 Natural White	Coating	0.77	0.74	0.85	Y	Y	Yes	35
BASF Corporation	Fluoroceram	818A7 Lead Cote	Coating	0.29	0.32	0.85	N	Y	Yes	35
BASF Corporation	Fluoroceram	818A94 Preweather Galvalume	Coating	0.26	0.26	0.85	N	Y	No	30
BASF Corporation	Fluoroceram	818R68	Coating	0.40	0.44	0.86	N	Y	Yes	35
BASF Corporation	Fluoroceram	818T7 Champagne	Coating	0.35	0.39	0.86	N	Y	Yes	35
BASF Corporation	Fluoroceram	836W29	Coating	0.63	0.61	0.85	N	Y		30
BASF Corporation	Fluoroceram	Almond 815V45	Coating	0.51	0.52	0.86	N	Y	Yes	35
BASF Corporation	Fluoroceram	Almond 815V45	Coating	0.51	0.52	0.86	N	Y		35
BASF Corporation	Fluoroceram	Ash Gray	Coating	0.36	0.35	0.87	N	Y	Yes	35
BASF Corporation	Fluoroceram	Ashtray 815D476	Coating	0.36	0.35	0.87	N	Y		35
BASF Corporation	Fluoroceram	Bone 815W178	Coating	0.67	0.67	0.85	N	Y	Yes	35
BASF Corporation	Fluoroceram	Bone 815W178	Coating	0.67	0.67	0.85	Y	Y		30
BASF Corporation	Fluoroceram	Copper 818R8	Coating	0.42	0.39	0.87	N	Y	Yes	35
BASF Corporation	Fluoroceram	Copper 818R8	Coating	0.42	0.39	0.87	N	Y		35
BASF Corporation	Fluoroceram	Gray 815D224	Coating	0.28	0.28	0.85	N	Y	Yes	35
BASF Corporation	Fluoroceram	Gray 815D224	Coating	0.28	0.28	0.85	N	Y		30
BASF Corporation	Fluoroceram	Gray 815D225	Coating	0.34	0.35	0.87	N	Y	Yes	35
BASF Corporation	Fluoroceram	Gray 815D225	Coating	0.34	0.35	0.87	N	Y		35
BASF Corporation	Fluoroceram	Green 815G282	Coating	0.39	0.39	0.85	N	Y	Yes	35
BASF Corporation	Fluoroceram	Green 815G282	Coating	0.39	0.39	0.85	N	Y		35
BASF Corporation	Fluoroceram	Green 815G774	Coating	0.28	0.25	0.83	N	Y	Yes	35
BASF Corporation	Fluoroceram	Green 815G774	Coating	0.28	0.25	0.83	N	Y		35
BASF Corporation	Fluoroceram	Marine Green 815G136	Coating	0.32	0.31	0.83	N	Y	Yes	35
BASF Corporation	Fluoroceram	Marine Green 815G136	Coating	0.32	0.31	0.85	N	Y		35
BASF Corporation	Fluoroceram	Parchment 815T116	Coating	0.35	0.37	0.86	N	Y	Yes	35
BASF Corporation	Fluoroceram	Parchment 815T116	Coating	0.35	0.37	0.86	N	Y		35
BASF Corporation	Fluoroceram	Red 815R130	Coating	0.33	0.33	0.83	N	Y	Yes	35
BASF Corporation	Fluoroceram	Red 815R130	Coating	0.33	0.33	0.83	N	Y		35
BASF Corporation	Fluoroceram	Red 815R153	Coating	0.42	0.40	0.86	N	Y	Yes	35
BASF Corporation	Fluoroceram	Red 815R153	Coating	0.42	0.40	0.86	N	Y		35
BASF Corporation	Fluoroceram	Sand 815T940	Coating	0.43	0.43	0.85	N	Y	Yes	35
BASF Corporation	Fluoroceram	Sand 815T940	Coating	0.43	0.43	0.85	N	Y		35
BASF Corporation	Fluoroceram	Silver 818A11	Coating	0.45	0.47	0.84	N	Y	Yes	35
BASF Corporation	Fluoroceram	Silver 818A11	Coating	0.45	0.47	0.84	N	Y		30
BASF Corporation	Fluoroceram	Tan 815T702	Coating	0.35	0.34	0.84	N	Y	Yes	35
BASF Corporation	Fluoroceram	Tan 815T702	Coating	0.35	0.34	0.84	N	Y		35
BASF Corporation	Fluoroceram	Terra Cotta 815R195	Coating	0.32	0.34	0.82	N	Y	Yes	35
BASF Corporation	Fluoroceram	Terracotta 815R195	Coating	0.32	0.34	0.82	N	Y		35
BaySystems North America, LLC	EverSil	ES580	Coating	0.74	0.71	0.85	Y	Y	Yes	10
BaySystems North America, LLC	Evercoat	EC 700	Coating	0.81	0.64	0.90	Y	N		10
BaySystems North America, LLC	Evercoat	EC500	Coating	0.86	0.62	0.89	Y	N		10
BaySystems North America, LLC	Evercoat	EC5400	Coating	0.86	0.66	0.90	Y	N		10
Berridge Manufacturing Company	Berridge	815G105 Hemlock Green	Coating	0.29	0.31	0.84	N	Y	Yes	20
Berridge Manufacturing Company	Berridge	815G34 Patina Green	Coating	0.32	0.34	0.85	N	Y	Yes	20
Berridge Manufacturing Company	Berridge	815R1 Terra Cotta	Coating	0.31	0.32	0.86	N	Y	Yes	20
Berridge Manufacturing Company	Berridge	815R153 Deep Red	Coating	0.42	0.40	0.84	N	Y	Yes	20
Berridge Manufacturing Company	Berridge	815T702 Sierra Tan	Coating	0.35	0.34	0.84	N	Y	Yes	20
Berridge Manufacturing Company	Berridge	815W32 Shasta White	Coating	0.54	0.54	0.84	N	Y	Yes	20
Berridge Manufacturing Company	Berridge	815W42 Parchment	Coating	0.46	0.49	0.85	N	Y	Yes	20

Berridge Manufacturing Company	Berridge	815W49 Natural White	Coating	0.77	0.74	0.85	N	Y	Yes	20
Berridge Manufacturing Company	Berridge	818A7 Lead Cote	Coating	0.29	0.32	0.85	N	Y	Yes	20
Berridge Manufacturing Company	Berridge	818A94 Preweathered Galvalume	Coating	0.26	0.26	0.85	N	Y	No	20
Berridge Manufacturing Company	Berridge	818R68 Copper Cote	Coating	0.40	0.44	0.86	N	Y	Y	20
Berridge Manufacturing Company	Berridge	818T7 Champagne	Coating	0.35	0.39	0.86	N	Y	Yes	20
Capstone Manufacturing LLC	TC Ceramic HB	33150	Coating	0.84	0.82	0.94	Y	Y		10
Capstone Manufacturing LLC	TC Ceramic HB	Standard	Coating	0.83	0.80	0.94	Y	Y		10
Cerama-Tech International	Cerama-Tech	Cerama-Tech	Coating	0.83	0.78	0.90	Y	Y	No	15
CertainTeed Corporation	CertainTeed	FlintCoat-A 300	Coating	0.66	0.56	0.37	Y	N		1- 10
CertainTeed Corporation	CertainTeed	FlintCoat-A Plus	Coating	0.70	0.56	0.40	Y	N		1- 10
CertainTeed Corporation	CertainTeed	FlintCoat-W	Coating	0.85	0.68	0.91	Y	N		1- 10
Conklin Company, Inc.	Benchmark	White Acrylic Top Coat	Coating	0.86	0.80	0.89	Y	N		12
Conklin Company, Inc.	Rapid Roof HV	White Acrylic Top Coat	Coating	0.73	0.55	0.76	Y	N		10
Conklin Company, Inc.	Rapid Roof LLI	White Acrylic Top Coat	Coating	0.85	0.55	0.90	Y	N		10
Custom-Bilt Metals	Titan	815D476 Ashtray	Coating	0.36	0.35	0.87	N	Y	Y	Lifetime
Custom-Bilt Metals	Titan	815G774 Leaf Green	Coating	0.28	0.25	0.83	N	Y	Y	Lifetime
Custom-Bilt Metals	Titan	815R195 Terracotta	Coating	0.32	0.34	0.82	N	Y	Y	Lifetime
Custom-Bilt Metals	Titan	815T940 Sand Beige	Coating	0.43	0.43	0.85	N	Y	Y	Lifetime
Custom-Bilt Metals	Titan	Redmix Red	Coating	0.33	0.33	0.84	N	Y	Y	Lifetime
Dimensional Metals Inc.	DMI	Acrylume	Coating	0.67	0.55	0.14	N	Y	No	20
Dimensional Metals Inc.	DMI	Beige	Coating	0.37	0.37	0.88	N	Y	No	20
Dimensional Metals Inc.	DMI	Champagne (platinum)	Coating	0.36	0.36	0.86	N	Y	No	20
Dimensional Metals Inc.	DMI	Colonial Red	Coating	0.26	0.26	0.87	N	Y	No	20
Dimensional Metals Inc.	DMI	Dove Grey	Coating	0.38	0.36	0.85	N	Y	No	20
Dimensional Metals Inc.	DMI	Metallic Copper	Coating	0.37	0.37	0.85	N	Y	No	20
Dimensional Metals Inc.	DMI	Metallic Silver	Coating	0.48	0.49	0.85	N	Y	No	20
Dimensional Metals Inc.	DMI	Patina Copper	Coating	0.47	0.47	0.87	N	Y	No	20
Dimensional Metals Inc.	DMI	Putty	Coating	0.61	0.60	0.87	N	Y	No	20
Dimensional Metals Inc.	DMI	Regal Red	Coating	0.40	0.39	0.87	N	Y	No	20
Dimensional Metals Inc.	DMI	Sandstone	Coating	0.55	0.55	0.87	N	Y	No	20
Dimensional Metals Inc.	DMI	Stone	Coating	0.33	0.32	0.87	N	Y	No	20
Dimensional Metals Inc.	DMI	TERRA COTTA	Coating	0.32	0.57	0.86	N	Y	No	20
Dimensional Metals Inc.	DMI	White	Coating	0.71	0.69	0.87	Y	Y	No	20
Diversified Products, LLC	Cool Roof In A Bucket	White	Coating	0.83	0.75	0.88	Y	N	No	5-20
Dura Coat Products Inc.	Durapon 70	DC190G-20	Coating	0.37	0.37	0.85	N	Y	Yes	35
Dura Coat Products Inc.	Durapon 70	DC190T-26	Coating	0.44	0.45	0.87	N	Y	Yes	35
Dura Coat Products Inc.	Durapon 70	DC190T-29	Coating	0.32	0.36	0.87	N	Y	Yes	35
Dura Coat Products Inc.	Durapon 70	DC190T-39	Coating	0.72	0.72	0.87	N	Y	Yes	35
Dura Coat Products Inc.	Durapon 70	DC190W-25	Coating	0.72	0.73	0.85	N	Y	Yes	35
Dura Coat Products Inc.	Durapon 70	DC190W-31	Coating	0.73	0.72	0.84	N	Y	Yes	35
Dura Coat Products Inc.	Durapon 70	DC190W-40	Coating	0.69	0.70	0.87	N	Y	Yes	35
Dura Coat Products Inc.	Durapon 70	DC190W-47	Coating	0.70	0.71	0.87	N	Y	Yes	35
Dura Coat Products Inc.	Durapon 70	DC191W-14	Coating	0.76	0.76	0.85	N	Y	Yes	35
Ecostar Science and Technology, Inc.	InfraLastic	Radiant Barrier Coating (RBC)	Coating	0.86	0.63	0.71	Y	Y	Yes	5
Elastomeric Roofing Systems, Inc.	ERS	Eraguard 1000	Coating	0.82	0.65	0.94	Y	N	No	10 - 15
Elastomeric Roofing Systems, Inc.	ERS	Eraguard 500	Coating	0.82	0.65	0.89	Y	N	No	10 - 15
Elastomeric Roofing Systems, Inc.	ERS	Eraguard Foam	Coating	0.73	0.61	0.94	Y	Y	Yes	10-15
Elastomeric Roofing Systems, Inc.	ERS	Eraguard Metal	Coating	0.74	0.62	0.94	Y	N	No	10-15
Elastomeric Roofing Systems, Inc.	ERS	Erakote	Coating	0.77	0.65	0.94	Y	N	No	10 - 15
Elastomeric Roofing Systems, Inc.	ERS	Eraithane Ultra	Coating	0.85	0.67	0.94	Y	Y		3
Elastomeric Roofing Systems, Inc.	ERS	Erlastic	Coating	0.82	0.76	0.94	Y	N	No	3
Elastomeric Roofing Systems, Inc.	ERS	Ethane 300 Finish Coat	Coating	0.65	0.60	0.48	Y	N	No	10 - 15
Elastomeric Roofing Systems, Inc.	ERS	Kynakote	Coating	0.86	0.72	0.87	Y	N	No	10
Fabral	All Profiles	Galvalume Unpainted	Coating	0.87	0.58	0.06	Y	Y		20
Fabral	All Profiles	Galvalume Clear Acrylic Coated	Coating	0.68	0.55	0.14	Y	Y		20
Fabral	Architectural Profiles	Apothecary Blue V32	Coating	0.26	0.26	0.85	N	Y	No	20
Fabral	Architectural Profiles	Arcadia Green SR	Coating	0.34	0.33	0.88	N	Y	No	20
Fabral	Architectural Profiles	Arctic White SR	Coating	0.56	0.55	0.84	N	Y	No	20
Fabral	Architectural Profiles	Ash Gray SR	Coating	0.39	0.39	0.85	N	Y	No	20
Fabral	Architectural Profiles	Bone White SR	Coating	0.72	0.70	0.84	Y	Y	No	20
Fabral	Architectural Profiles	Brick Red SR	Coating	0.29	0.29	0.87	N	Y	No	20

Fabral	Architectural Profiles	Bright Silver SR	Coating	0.60	0.60	0.77	N	Y	No	20
Fabral	Architectural Profiles	Brownstone SR	Coating	0.38	0.38	0.85	N	Y	No	20
Fabral	Architectural Profiles	Copper Penny SR	Coating	0.43	0.42	0.83	N	Y	No	20
Fabral	Architectural Profiles	Forest Green SR	Coating	0.27	0.26	0.85	N	Y	No	20
Fabral	Architectural Profiles	Old Town Gray V13	Coating	0.25	0.25	0.90	N	Y		20
Fabral	Architectural Profiles	Regal Red SR	Coating	0.42	0.41	0.84	N	Y	No	20
Fabral	Architectural Profiles	Regal White SR	Coating	0.70	0.68	0.84	Y	Y	No	20
Fabral	Architectural Profiles	Sandstone SR	Coating	0.51	0.50	0.85	N	Y	No	20
Fabral	Architectural Profiles	Sierra Gold SR	Coating	0.47	0.46	0.86	N	Y	No	20
Fabral	Architectural Profiles	Sierra Tan V70	Coating	0.38	0.39	0.90	N	Y		20
Fabral	Architectural Profiles	Terra Cotta SR	Coating	0.35	0.35	0.87	N	Y	No	20
Fabral	Wood Frame Profiles	Ash Gray 548	Coating	0.37	0.37	0.89	N	Y		30
Fabral	Wood Frame Profiles	Caribbean Blue 584	Coating	0.25	0.25	0.90	N	Y		30
Fabral	Wood Frame Profiles	Hickory Moss 572	Coating	0.32	0.32	0.90	N	Y		30
Fabral	Wood Frame Profiles	Light Stone 588	Coating	0.47	0.48	0.89	N	Y		30
Fabral	Wood Frame Profiles	Patina Green 593	Coating	0.37	0.38	0.90	N	Y		30
Fabral	Wood Frame Profiles	Polar White 560	Coating	0.63	0.62	0.89	N	Y		30
Fabral	Wood Frame Profiles	White 299	Coating	0.58	0.57	0.89	N	Y		30
Firestone Building Products Company	Firestone	Firestone Aluminum Fibered Roof Coating	Coating	0.74	0.51	0.38	Y	N	No	20
Firestone Building Products Company	Firestone Building Products	AcryliTop PC-100 (White)	Coating	0.81	0.66	0.87	Y	N	No	5
GACO Western	GACOFLEX	A3200	Coating	0.82	0.53	0.89	Y	N	No	10 - 15
GACO Western	GACOSIL	S1000	Coating	0.89	0.56	0.89	Y	N	No	10 - 15
GAF Materials Corporation	LeakBuster	Matrix 322	Coating	0.87	0.69	0.87	Y	Y	No	5
GAF Materials Corporation	LeakBuster	Matrix 602	Coating	0.84	0.59	0.90	Y	Y	No	10
GAF Materials Corporation	LeakBuster	Matrix 715	Coating	0.83	0.74	0.88	Y	Y	No	10
GAF Materials Corporation	Topcoat	EPDM	Coating	0.86	0.70	0.88	Y	N	No	10
GAF Materials Corporation	Topcoat	Elastomeric Roofing Membrane	Coating	0.85	0.68	0.90	Y	N	No	10
GAF Materials Corporation	Topcoat	Fireshield MB	Coating	0.72	0.69	0.91	Y	N	No	10
GAF Materials Corporation	Topcoat	Fireshield SB	Coating	0.81	0.71	0.90	Y	N	No	10
GAF Materials Corporation	Topcoat	Fireshield WB EPDM	Coating	0.75	0.67	0.90	Y	N	No	10
GAF Materials Corporation	Topcoat	MB Plus	Coating	0.83	0.74	0.88	Y	N	No	10
GAF Materials Corporation	Topcoat	Surface Seal SB	Coating	0.84	0.59	0.90	Y	N	No	10
Gardner-Gibson	APOC	211 Non-Fibered Aluminium Coating	Coating	0.68	0.59	0.40	Y	Y		5
Gardner-Gibson	APOC	212 Fibered Aluminum Coating	Coating	0.67	0.57	0.42	Y	Y	No	5
Gardner-Gibson	APOC	252 Sun-White Elastomeric	Coating	0.81	0.67	0.87	Y	Y		
Gardner-Gibson	APOC	258 EPDM Renew-It Elastomeric	Coating	0.82	0.78	0.89	Y	Y		10
Gardner-Gibson	APOC	247 White Sun Shields Elastomeric	Coating	0.79	0.65	0.87	Y	Y		7
Gardner-Gibson	APOC	248 Arizona White Elastomeric	Coating	0.78	0.70	0.89	Y	Y		5 - 10
Gardner-Gibson	APOC	AP-273 Gray	Coating	0.76	0.60	0.89	Y	Y	No	10
Gardner-Gibson	APOC	AP-274 Tan	Coating	0.70	0.64	0.86	Y	Y	No	10
Gardner-Gibson	Black Jack	700 Roof Guard	Coating	0.85	0.65	0.86	Y	Y	No	10
Gardner-Gibson	Black Jack	Roof Gard 700	Coating	0.85	0.65	0.87	Y	Y	No	7
Gardner-Gibson	Sta-Kool	770 White Elastomeric	Coating	0.79	0.65	0.87	Y	Y		7
Gardner-Gibson	Sta-Kool	780 White Elastomeric	Coating	0.78	0.70	0.89	Y	Y		5 - 10
General Coatings, Inc.	Ultra-Flex	1000 High Tensile	Coating	0.89	0.69	0.90	Y	N	No	5 - 10
General Coatings, Inc.	Ultra-Flex	1000 High Tensile w/ White Granules	Coating	0.89	0.69	0.90	Y	N	No	5 - 10
General Coatings, Inc.	Ultra-Flex	1000 High Tensile w/ white granules	Coating	0.89	0.69	0.90	Y	Y	No	5 - 10
General Coatings, Inc.	Ultra-Flex	1000 Standard	Coating	0.84	0.67	0.90	Y	N	No	5 - 10
General Coatings, Inc.	Ultra-Flex	1000 w/ White Granules	Coating	0.84	0.67	0.90	Y	N	No	5 - 10
General Coatings, Inc.	Ultra-Flex	1600	Coating	0.83	0.69	0.90	Y	N	No	5 - 10
General Coatings, Inc.	Ultra-Shield	3000	Coating	0.84	0.65	0.90	Y	N	No	10
General Coatings, Inc.	UltraGard	5500	Coating	0.87	0.63	0.89	Y	N	No	5 - 10
GH International	Excel	EPM-6	Coating	0.78	0.64	0.92	Y	Y	No	
Global Encasement Inc.	Roofcoat	White	Coating	0.83	0.69	0.94	Y	N	No	5 - 20
Global Encasement Inc.	Roofcoat II	White	Coating	0.83	0.69	0.94	Y	N	No	5 - 20
Henry Company	Henry	280	Coating	0.76	0.62	0.86	Y	N	No	10
Henry Company	Henry	587	Coating	0.84	0.72	0.91	Y	N	No	10
Henry Company	Henry	869	Coating	0.70	0.54	0.48	Y	N	No	5
Henry Company	Henry	SolarFlex 287	Coating	0.84	0.74	0.86	Y	Y	No	7
Henry Company	Henry	SolarFlex 287 SF	Coating	0.84	0.74	0.82	Y	Y	No	7
Henry Company	Metalshield	275	Coating	0.76	0.62	0.84	Y	N	No	10
Henry Company	Prograde	550	Coating	0.76	0.62	0.87	Y	N	No	10
Henry Company	Rubberkote	827	Coating	0.76	0.62	0.84	Y	N	No	10
Hydro-Stop, Inc.	PremiumCoat Finish Cotton	2003-125	Coating	0.71	0.60	0.90	Y	Y	No	10
Hydro-Stop, Inc.	PremiumCoat Finish White	2003-015	Coating	0.79	0.67	0.90	Y	Y	No	10
Hyload, Inc.	Hyload	Alproof/Alpsam	Coating	0.74	0.72	0.94	Y	N	Yes	20
Inland Coatings Corporation	Inland Coatings	RC-2000 White	Coating	0.82	0.72	0.89	Y	Y		10

Inseco Inc.	Inseco	Dura-Loc MST 100 ES	Coating	0.90	0.79	0.88	Y	Y	No	7
Insulating Coatings Corporation	ASTEC	900	Coating	0.85	0.75	0.90	Y	N	No	10
Insulating Coatings Corporation	ASTEC	2000	Coating	0.85	0.73	0.90	Y	N	Yes	10
Intellocoat Technologies, LLC	Intellocoat Technologies LLC	Solar Save	Coating	0.88	0.79	0.90	Y	Y		10
Isothermal Protective Coatings, Inc.	Acrylink G Roofing Systems	Acrysheen Surface Coating	Coating	0.80	0.79	0.94	Y	Y	Yes	5-20
Isothermal Protective Coatings, Inc.	IPC	Acrylink G	Coating	0.79	0.72	0.95	Y	Y	No	5 - 20
Johns Manville Corporation	Dibiten	TopGard24	Coating	0.83	0.75	0.88	Y	N	No	
Johns Manville Corporation	TopGard 4000	White	Coating	0.83	0.75	0.88	Y	N	No	
Johns Manville Corporation	TopGard 5000	White	Coating	0.83	0.75	0.88	Y	N	No	
Karnak Corporation	Karnak	298 Alumin-R	Coating	0.68	0.61	0.40	Y	N	No	3
Karnak Corporation	Karnak	501 Elasto-Brite	Coating	0.86	0.77	0.91	Y	N		3
Karnak Corporation	Karnak	502 RCW Elasto-Kote	Coating	0.85	0.72	0.89	Y	N	No	3
Karnak Corporation	Karnak	505 Elasto Brite M	Coating	0.68	0.61	0.40	Y	N	No	3
Karnak Corporation	Karnak	98AF	Coating	0.70	0.61	0.37	Y	N	No	3
KST Coatings Manufacturing, Inc.	Kool Seal	63-300	Coating	0.86	0.61	0.91	Y	Y		7
KST Coatings Manufacturing, Inc.	Kool Seal	63-450	Coating	0.86	0.61	0.90	Y	Y		7
KST Coatings Manufacturing, Inc.	Kool Seal	63-600	Coating	0.87	0.61	0.90	Y	Y		10
KST Coatings Manufacturing, Inc.	Kool Seal	63-705	Coating	0.86	0.63	0.88	Y	Y	No	10
KST Coatings Manufacturing, Inc.	Kool Seal	63-800	Coating	0.86	0.63	0.88	Y	Y	No	10
KST Coatings Manufacturing, Inc.	MAX White Kool Seal	64-700	Coating	0.85	0.58	0.90	Y	Y		10
KST Coatings Manufacturing, Inc.	Snow Roof Systems	Mobile Coat	Coating	0.75	0.54	0.90	Y	N	No	5
KST Coatings Manufacturing, Inc.	Snow Roof Systems	Roofer's Best	Coating	0.75	0.54	0.90	Y	N		5
KST Coatings Manufacturing, Inc.	Snow Roof Systems	Snow Roof	Coating	0.85	0.62	0.89	Y	N		10
LANCO Manufacturing Corporation	Lanco Manufacturing Co.	White Seal/RC-865	Coating	0.88	0.75	0.89	Y	N	No	10
LaPolla Industries, Inc.	LaPolla Coatings	Restoration Coating System RCS 5001/White	Coating	0.85	0.78	0.90	Y	Y	Yes	5-15
LaPolla Industries, Inc.	LaPolla Coatings	Therm-O-Flex TF 1001 / White	Coating	0.84	0.78	0.90	Y	N	No	5 - 10
Liquid Plastics, Inc.	Decothane SP	White	Coating	0.83	0.52	0.91	Y	N	Yes	30
Master Paints and Chemicals	Masterflex	Coating	Coating	0.75	0.65	0.89	Y	N	No	5
MEGA Industries Corporation	MegaFLEX	M-100 Cool Roof White	Coating	0.86	0.70	0.94	Y	N	No	5 - 10
Metacrylics	Metacrylics	Acrylic White	Coating	0.87	0.71	0.90	Y	N	No	10
MFM Building Products Corporation	MFM	Peel & Seal Aluminum	Coating	0.90	0.75	0.05	Y	N	No	10
Mueller, Inc.	CERAM-A-STAR 900	SA3X33318	Coating	0.35	0.35	0.88	N	Y	No	25
Mueller, Inc.	CERAM-A-STAR 900	SW3X32695	Coating	0.60	0.60	0.87	N	Y	No	25
Mueller, Inc.	CERAM-A-STAR 940	SR3P32680	Coating	0.40	0.40	0.87	N	Y	No	25
Mueller, Inc.	TRINAR	KR3R86913	Coating	0.37	0.38	0.87	N	Y	No	25
National Coatings Corporation	AcryShield	A400	Coating	0.83	0.75	0.88	Y	N	No	5 - 20
National Coatings Corporation	AcryShield	A400 White-Granulated	Coating	0.71	0.54	0.95	Y	N	No	5 - 20
National Coatings Corporation	AcryShield	A500	Coating	0.83	0.73	0.88	Y	N	No	5 - 20
National Coatings Corporation	AcryShield	A500 White-Granulated	Coating	0.71	0.54	0.95	Y	N	No	5 - 20
National Coatings Corporation	AcryShield	A510	Coating	0.84	0.61	0.92	Y	N	No	5 - 20
National Coatings Corporation	AcryShield	A510 White-Granulated	Coating	0.71	0.54	0.95	Y	N		5 - 20
National Coatings Corporation	AcryShield	A520	Coating	0.83	0.73	0.88	Y	N	No	5 - 20
National Coatings Corporation	AcryShield	A550	Coating	0.86	0.81	0.88	Y	N	No	5 - 20
National Coatings Corporation	AcryShield	A550 White-Granulated	Coating	0.71	0.54	0.95	Y	N	No	5 - 20
National Coatings Corporation	AcryShield	A600	Coating	0.83	0.76	0.88	Y	N	No	5 - 20
National Coatings Corporation	AcryShield	A600 White-Granulated	Coating	0.71	0.54	0.95	Y	N	No	5 - 20
National Coatings Corporation	AcryShield	AcryShield A420	Coating	0.83	0.76	0.88	Y	N	No	5-20
National Polymers Incorporated	National Polymers	NP811FP	Coating	0.81	0.78	0.87	Y	Y		5 - 10
National Polymers Incorporated	National Polymers	NP814	Coating	0.83	0.80	0.89	Y	Y	Yes	5
Nationwide Chemical Coatings Manufacturers Inc.	Nationwide	Insulkote	Coating	0.82	0.72	0.94	Y	Y		8
Nationwide Chemical Coatings Manufacturers Inc.	Nationwide	Permakote	Coating	0.83	0.74	0.93	Y	Y		12

Nationwide Chemical Coatings Manufacturers Inc.	Nationwide	Permakote Plus	Coating	0.81	0.72	0.94	Y	Y		6-12
Nationwide Chemical Coatings Manufacturers Inc.	Nationwide	Snowbrite	Coating	0.84	0.70	0.94	Y	Y		6
Nationwide Chemical Coatings Manufacturers Inc.	Nationwide	Ultra Kote	Coating	0.83	0.73	0.93	Y	Y		10
Nationwide Chemical Coatings Manufacturers Inc.	Nationwide	Ultra Kote XL	Coating	0.82	0.72	0.94	Y	Y		10
Nationwide Chemical Coatings Manufacturers Inc.	Nationwide	Ultra Seal	Coating	0.82	0.73	0.92	Y	Y		10
New Process Steel	New Process	950 Lightstone	Coating	0.52	0.51	0.87	N	Y	No	30
Pacific Polymers International Inc.	Pacific Polymers International, Inc.	Elasto-Deck 6500	Coating	0.89	0.88	0.88	Y	N	No	5-15
Pacific Polymers International Inc.	Pacific Polymers International, Inc.	Elasto-Tex Roof Coating	Coating	0.83	0.82	0.88	Y	N	No	15
Palmer Asphalt Company	Bulldog	Durex	Coating	0.85	0.70	0.90	Y	Y		5 - 10
Performance Roof Systems, Inc.	PermaCool	Reflective Roof Coating	Coating	0.86	0.70	0.94	Y	N	No	5 - 10
Permasield Coatings, Inc.	Permasield	PC-50	Coating	0.85	0.60	0.89	Y	N	No	15
Permasield Coatings, Inc.	Permasield	PC-60	Coating	0.84	0.60	0.89	Y	N	No	15
Pinturas Termicas del Norte	Hidrocoat	Gold	Coating	0.86	0.80	0.89	Y	Y	Yes	7
Pinturas Termicas del Norte	Hidrocoat	Platinum	Coating	0.87	0.74	0.89	Y	Y	Yes	10
Pinturas Termicas del Norte	Hidrocoat	Silver	Coating	0.87	0.70	0.90	Y	Y	Yes	5
Pinturas Termicas del Norte	Raintek	Double Action	Coating	0.86	0.80	0.89	Y	Y	Yes	5
Pinturas Termicas del Norte	Raintek	MAX 10	Coating	0.87	0.74	0.90	Y	Y	Yes	10
Pinturas Termicas del Norte	Raintek	Raincoat	Coating	0.87	0.70	0.90	Y	Y	Yes	5
Pinturas Termicas del Norte	Thermotek	Doble Accion	Coating	0.88	0.80	0.89	Y	Y	Yes	5
Pinturas Termicas del Norte	Thermotek	Imper	Coating	0.87	0.70	0.89	Y	Y	Yes	3
Pinturas Termicas del Norte	Thermotek	Max 10	Coating	0.87	0.74	0.89	Y	Y	Yes	10
Polarhide	Polarhide	Polarhide	Coating	0.84	0.75	0.87	Y	Y	Yes	20
Ponderosa Paint Co., Inc.	Galacti-Kote	200104	Coating	0.86	0.54	0.88	Y	Y	No	5
PPG Industries, Inc.	Duramar SPF	5MR54054	Coating	0.47	0.47	0.85	N	Y	No	20
PPG Industries, Inc.	Duramar SPF	5VMA59131P	Coating	0.59	0.59	0.86	N	Y	No	20
PPG Industries, Inc.	Duramar SPF	SPF82153	Coating	0.35	0.35	0.86	N	Y	No	20
PPG Industries, Inc.	Duramar SPF	SPF82160	Coating	0.27	0.27	0.87	N	Y	No	20
PPG Industries, Inc.	Duramar SPF	SPF82161	Coating	0.27	0.27	0.86	N	Y	No	20
PPG Industries, Inc.	Duramar SPF	SPF82494	Coating	0.37	0.37	0.86	N	Y	No	20
PPG Industries, Inc.	Duramar SPF	SPF82496P	Coating	0.26	0.26	0.85	N	Y	No	20
PPG Industries, Inc.	Duramar SPF	SPF82591	Coating	0.28	0.28	0.86	N	Y	No	20
PPG Industries, Inc.	Duramar SPF	SPF82599P	Coating	0.28	0.28	0.86	N	Y	No	20
PPG Industries, Inc.	Duramar SPF	SPF83468 #12	Coating	0.65	0.56	0.86	N	Y	No	20
PPG Industries, Inc.	Duramar SPF	SPF83595	Coating	0.72	0.72	0.86	N	Y	No	20
PPG Industries, Inc.	Duramar SPF	SPF83652	Coating	0.31	0.31	0.86	N	Y	No	20
PPG Industries, Inc.	Duramar SPF	SPF839661XL	Coating	0.41	0.41	0.86	N	Y	No	20
PPG Industries, Inc.	Duramar SPF	SPF84120	Coating	0.73	0.73	0.85	N	Y	No	20
PPG Industries, Inc.	Duramar SPF	SPF84133	Coating	0.49	0.49	0.86	N	Y	No	20
PPG Industries, Inc.	Duramar SPF	SPF84158	Coating	0.55	0.55	0.86	N	Y	No	20
PPG Industries, Inc.	Duramar SPF	SPF84169P	Coating	0.33	0.33	0.86	N	Y	No	20
Prairie Technologies, Inc.	Prairie Technologies	PrairieGuard WBA	Coating	0.82	0.65	0.94	Y	N		10-15
Prairie Technologies, Inc.	Prairie Technologies	PrairieGuard WBA-A	Coating	0.82	0.76	0.89	Y	N		10-15
Prairie Technologies, Inc.	Prairie Technologies	PrairieGuard WBP	Coating	0.85	0.67	0.94	Y	N		10-15
Pro-Tech Products Inc.	100% Acrylic Roof Coating	Superiorseal White	Coating	0.85	0.78	0.88	Y	Y	No	5
Pro-Tech Products Inc.	Pro-tech	EC-100 Energy Star Tan	Coating	0.66	0.65	0.88	Y	Y	Yes	5
Pro-Tech Products Inc.	Pro-tech	EC-100 White	Coating	0.86	0.81	0.88	Y	Y	Yes	5
ProTek - USA	THERMCOTE	A-10	Coating	0.83	0.78	0.93	Y	N	No	10
ProTek - USA	THERMCOTE	A-5	Coating	0.84	0.78	0.94	Y	N	No	5
ProTek - USA	THERMCOTE	A-7	Coating	0.82	0.77	0.94	Y	N	No	7
ProTek - USA	THERMCOTE	A-PW5	Coating	0.81	0.77	0.94	Y	N	No	5 - 10
R.M. Lucas Co.	Lucas	#1000	Coating	0.84	0.66	0.88	Y	Y	No	5
R.M. Lucas Co.	Lucas	#5000	Coating	0.80	0.73	0.88	Y	Y	no	10
R.M. Lucas Co.	Lucas	#5700	Coating	0.80	0.73	0.88	Y	N	no	5
R.M. Lucas Co.	Lucas	#637	Coating	0.73	0.57	0.32	Y	N	No	
R.M. Lucas Co.	Lucas	#648	Coating	0.66	0.54	0.40	Y	Y	No	3
R.M. Lucas Co.	Lucas	#748	Coating	0.71	0.54	0.34	Y	Y	Yes	3
Republic Powdered Metals, Inc.	Alumanation 301	Aluminum Coating	Coating	0.68	0.50	0.42	Y	N		10 - 12
Republic Powdered Metals, Inc.	Geogard	Elastomeric, Urethane	Coating	0.84	0.69	0.82	Y	N		12
Republic Powdered Metals, Inc.	Solargard Elastomeric 6083	Coating	Coating	0.78	0.57	0.83	Y	Y	No	10
Republic Powdered Metals, Inc.	Solargard Hy-build	Water-based elastomeric coating	Coating	0.78	0.64	0.85	Y	N		10 - 30
Republic Powdered Metals, Inc.	Solargard Ultra	High Build Reflective Coating	Coating	0.84	0.60	0.78	Y	N		10
Resin Technology Company	Permax	110	Coating	0.85	0.71	0.90	Y	Y	No	10
Resin Technology Company	Permax	115	Coating	0.86	0.73	0.90	Y	Y	No	10
Resin Technology Company	Permax	2000	Coating	0.89	0.54	0.89	Y	Y	No	10
Resin Technology Company	Permax	Permax-108	Coating	0.86	0.56	0.90	Y	Y	No	10
Resin Technology Company	Permax	Permax-108 w/ White Granule Finish	Coating	0.72	0.69	0.94	Y	N	No	10
Resin Technology Company	Permax	Permax-115 w/ White Granule Finish	Coating	0.76	0.58	0.91	Y	N	No	10-20

Ryerson	BASF Fluoroceram	815W49 Natural White	Coating	0.77	0.74	0.85	N	Y		30
Saf-T-Screens, Inc., dba Roof Guardian Technologies, dba STS Coatings	Roof Guardian Technologies, Inc.	RG170	Coating	0.88	0.62	0.91	Y	Y	No	10
Sealoflex Inc.	Sealoflex	Finish Coat (White)	Coating	0.77	0.52	0.94	Y	Y	No	10
Siplast, Inc.	Siplast, Inc.	PC-227 Elastomeric Roof Coating	Coating	0.83	0.75	0.88	Y	N		5 - 10
SOLEC - Solar Energy Corporation	LO/MIT	LO/MIT-1	Coating	0.80	0.67	0.24	Y	N		1 - 5
Somay Products Inc	Somay	Roof Mastic 842-01	Coating	0.85	0.73	0.87	Y	N	No	5
Soprema, Inc.	Soprema Inc.	'R' NOVA Roof Coating	Coating	0.88	0.63	0.90	Y	N	No	10
SR Products Group	Wite Brite Elastomeric Coating	Wite Brite Elastomeric Roof Coating	Coating	0.81	0.70	0.88	Y	Y	Y	2
Structural Elastomeric Products, Inc.	E-las-tek	#100 Solar Mastic	Coating	0.86	0.77	0.89	Y	N		5
Structural Elastomeric Products, Inc.	E-las-tek	#109 Solar Magic	Coating	0.79	0.78	0.88	Y	N		4
Structural Elastomeric Products, Inc.	E-las-tek	#120 Solar Tek 2000	Coating	0.84	0.80	0.88	Y	N		6
Structural Elastomeric Products, Inc.	E-las-tek	Solar Magic	Coating	0.84	0.78	0.88	Y	N	No	4
Structural Elastomeric Products, Inc.	E-las-tek	Solar Mastic	Coating	0.85	0.77	0.89	Y	N	No	5
Structural Elastomeric Products, Inc.	E-las-tek	Solar TEK Extreme	Coating	0.87	0.80	0.88	Y	N	No	6
Superior Products International II, Inc.	Ceramic	Super Therm	Coating	0.80	0.79	0.90	Y	N		10-20
SWD Urethane Company	Kool-Kote	1929-F	Coating	0.81	0.72	0.91	Y	N		10
TAMKO Building Products, Inc.	TAM Star	White Coating	Coating	0.75	0.70	0.91	Y	Y	No	7
Tech Traders Inc.	Insuladd	E-Coat	Coating	0.85	0.75	0.81	Y	Y	Yes	10
Technical Roofing Solutions, Inc.	ACRY-TEK	4000	Coating	0.81	0.70	0.88	Y	Y	No	10
Technical Roofing Solutions, Inc.	ACRY-TEK	4200	Coating	0.80	0.69	0.86	Y	Y	No	10
Technical Roofing Solutions, Inc.	ACRY-TEK	5000	Coating	0.82	0.66	0.85	Y	Y	No	10
Technical Roofing Solutions, Inc.	ACRY-TEK	9000	Coating	0.85	0.66	0.85	Y	Y	No	10
Technical Roofing Solutions, Inc.	Poly-Sil	2200	Coating	0.84	0.66	0.85	Y	Y	No	10
Temp-Coat Brand Products, LLC	TEMP COAT	Roofing & Siding Coating	Coating	0.88	0.61	0.88	Y	Y	NA	10
The Brewer Company	Fortress	#5601 White Elastomeric Coating	Coating	0.83	0.71	0.84	Y	N	No	7
The Brewer Company	Storm King	#5651 White Elastomeric Roof Coating	Coating	0.75	0.70	0.84	Y	N	No	7
The Garland Company, Inc.	Pyramic	White Reflective Coating	Coating	0.83	0.75	0.88	Y	Y		1 - 10
The Garland Company, Inc.	WhiteKnight	Elastomeric Polyurethane Coating	Coating	0.77	0.63	0.88	Y	Y		10
The Ultimate Coatings Company	Eco-Therm Elastomeric	2500 White	Coating	0.82	0.81	0.90	Y	Y		10
Therma-Cote, Inc.	Thermacote Roofs	Thermacote Roofs	Coating	0.83	0.75	0.88	Y	N	Yes	10
ThorWorks Industries, Inc.	Cool King	Premium White Elastomeric	Coating	0.85	0.79	0.90	Y	N	No	10
ThorWorks Industries, Inc.	Cool King	Premium White Elastomeric	Coating	0.85	0.79	0.90	Y	N	No	7
ThorWorks Industries, Inc.	Seal Best	White Elastomeric Roof Coating	Coating	0.85	0.79	0.89	Y	N		7
TKO Waterproof Coatings, LLP	Metal I-kote	Bright White	Coating	0.69	0.67	0.84	Y	N	Yes	7
TKO Waterproof Coatings, LLP	ProCote	White	Coating	0.75	0.75	0.84	Y	N	Yes	7
TKO Waterproof Coatings, LLP	ProMetalCote	White	Coating	0.69	0.67	0.83	Y	N	Yes	7
TKO Waterproof Coatings, LLP	Roof-kote	Bright White	Coating	0.77	0.76	0.83	Y	N	Yes	7
Topps Products Inc.	Topps Seal	#9100	Coating	0.83	0.59	0.88	Y	Y	Yes	10
Tremco, Inc.	Double Duty Aluminum LV	Aluminum Coating	Coating	0.65	0.53	0.57	Y	N		10 - 12
Tremco, Inc.	One Coat Aluminum	Aluminum Coating	Coating	0.68	0.50	0.39	Y	N		10 - 12
Tremco, Inc.	Polarcote	Fire Retardant Coating	Coating	0.82	0.50	0.87	Y	N		10
Tremco, Inc.	TREMCO SRC	Elastomeric, Urethane	Coating	0.84	0.69	0.74	Y	N		12
Tremco, Inc.	Tremco	High Build Reflective Coating	Coating	0.84	0.60	0.83	Y	N		10
Tremco, Inc.	Trem-lite	Water-based Elastomeric	Coating	0.78	0.57	0.87	Y	N		10
Tropical Asphalt Products Corporation	Roofing	#901 Elastomeric Roof Coating	Coating	0.88	0.79	0.88	Y	N	Yes	3
Tropical Asphalt Products Corporation	Roofing	Eternalastic	Coating	0.86	0.79	0.98	Y	N	No	5

Tropical Asphalt Products Corporation	Roofing	Reflex 921	Coating	0.84	0.71	0.84	Y	Y	Yes	3
U.S. Ply, Inc.	USP Ceramamax Roof Coating	USP Ceramamax Roof Coating	Coating	0.80	0.79	0.96	Y	Y	No	10
U.S. Ply, Inc.	USP	Energy Brite	Coating	0.84	0.71	0.88	Y	Y	Yes	5
U.S. Ply, Inc.	USP	Energy Kote	Coating	0.88	0.57	0.91	Y	Y	Yes	10
U.S. Ply, Inc.	USP	EnergyMax	Coating	0.84	0.72	0.88	Y	Y	Yes	10
U.S. Ply, Inc.	USP All Season SEBS	USP All Season SEBS	Coating	0.82	0.61	0.95	Y	Y	No	5
U.S. Ply, Inc.	USP UltraStar Hi Reflect Coating	USP UltraStar Hi Reflect Coating	Coating	0.86	0.79	0.98	Y	N	No	5
Uniflex	UNIFLEX	41-300	Coating	0.88	0.57	0.91	Y	N		10
Uniflex	UNIFLEX	41-500	Coating	0.86	0.61	0.90	Y	N		5
United Asphalt Company, Inc.	United	Premium Fibered Aluminum Coating	Coating	0.70	0.50	0.38	Y	Y	No	5
United Coatings	Diathon	White	Coating	0.89	0.85	0.89	Y	N	No	5 - 15
United Coatings	Diathon HT	High Tensile White	Coating	0.82	0.72	0.89	Y	Y	No	5 - 15
United Coatings	Duragard	Duragard	Coating	0.77	0.71	0.89	Y	N	No	5, 10
United Coatings	Elastuff	102	Coating	0.81	0.68	0.89	Y	N	No	5 - 15
United Coatings	Roof Mate	Roof Mate White	Coating	0.85	0.57	0.89	Y	Y	No	5 - 15
United Coatings	Roof Mate HT	High Tensile White	Coating	0.82	0.72	0.89	Y	Y	No	5 - 15
United Coatings	Traffic Guard	Traffic Guard	Coating	0.77	0.71	0.89	Y	N	No	5, 10
Valspar Corporation	Fluropon	Aged Copper	Coating	0.47	0.46	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Almond	Coating	0.57	0.56	0.86	N	Y	No	30
Valspar Corporation	Fluropon	Almonde	Coating	0.60	0.57	0.84	N	Y	No	30
Valspar Corporation	Fluropon	Antique Patina	Coating	0.29	0.30	0.87	N	Y	No	30
Valspar Corporation	Fluropon	Apothecary Blue	Coating	0.26	0.26	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Arcadia Green	Coating	0.34	0.33	0.88	N	Y	No	30
Valspar Corporation	Fluropon	Arctic White	Coating	0.56	0.55	0.84	N	Y	No	30
Valspar Corporation	Fluropon	Ash Gray	Coating	0.39	0.39	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Beige	Coating	0.40	0.39	0.86	N	Y	No	30
Valspar Corporation	Fluropon	Bone White	Coating	0.72	0.70	0.84	Y	Y	No	30
Valspar Corporation	Fluropon	Brandywine	Coating	0.25	0.23	0.85	N	Y	No	10
Valspar Corporation	Fluropon	Brick Red	Coating	0.29	0.29	0.87	N	Y	No	30
Valspar Corporation	Fluropon	Bright Silver	Coating	0.59	0.60	0.80	N	Y	no	30
Valspar Corporation	Fluropon	Brite Red	Coating	0.32	0.34	0.79	N	Y	No	10
Valspar Corporation	Fluropon	Brownstone	Coating	0.38	0.38	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Champagne	Coating	0.37	0.36	0.83	N	Y	No	30
Valspar Corporation	Fluropon	Champagne Gold	Coating	0.48	0.48	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Champagne Pearl	Coating	0.48	0.48	0.81	N	Y	No	30
Valspar Corporation	Fluropon	Chromium Gray	Coating	0.48	0.44	0.85	N	Y	No	30
Valspar Corporation	Fluropon	City Scape	Coating	0.37	0.34	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Classic Green	Coating	0.27	0.26	0.83	N	Y	No	30
Valspar Corporation	Fluropon	Clay	Coating	0.33	0.32	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Colonial Red	Coating	0.27	0.23	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Copper Metallic	Coating	0.45	0.44	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Copper Penny	Coating	0.43	0.42	0.83	N	Y	No	30
Valspar Corporation	Fluropon	Egyptian White	Coating	0.54	0.53	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Forest Green	Coating	0.27	0.26	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Granite	Coating	0.36	0.35	0.84	N	Y	No	30
Valspar Corporation	Fluropon	Herringbone	Coating	0.63	0.63	0.86	N	Y	No	30
Valspar Corporation	Fluropon	Ivory	Coating	0.67	0.65	0.87	Y	Y	No	30
Valspar Corporation	Fluropon	Khaki	Coating	0.42	0.42	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Lee Ivory	Coating	0.64	0.62	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Light Gray	Coating	0.54	0.55	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Light Stone	Coating	0.50	0.50	0.86	N	Y	No	30
Valspar Corporation	Fluropon	Linen White	Coating	0.72	0.71	0.84	Y	Y	No	30
Valspar Corporation	Fluropon	Mansard Brown	Coating	0.26	0.29	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Matte Black	Coating	0.27	0.27	0.86	N	Y	No	30
Valspar Corporation	Fluropon	Metallic Silver	Coating	0.60	0.60	0.77	N	Y	No	30
Valspar Corporation	Fluropon	Natural Patina	Coating	0.39	0.39	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Off White	Coating	0.71	0.67	0.85	Y	Y	No	30
Valspar Corporation	Fluropon	Parchment	Coating	0.54	0.53	0.86	N	Y	No	30
Valspar Corporation	Fluropon	Patina Green	Coating	0.26	0.28	0.88	N	Y	No	30
Valspar Corporation	Fluropon	Patriot Red	Coating	0.42	0.41	0.84	N	Y	No	30
Valspar Corporation	Fluropon	Portland Stone	Coating	0.45	0.44	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Rawhide	Coating	0.53	0.51	0.86	N	Y	No	30
Valspar Corporation	Fluropon	Regal Red	Coating	0.36	0.36	0.83	N	Y	No	30
Valspar Corporation	Fluropon	Regal White	Coating	0.70	0.68	0.84	Y	Y	No	30
Valspar Corporation	Fluropon	Sandstone	Coating	0.51	0.50	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Sandstone Metallic	Coating	0.47	0.46	0.80	N	Y	No	30
Valspar Corporation	Fluropon	Sandstone SR	Coating	0.54	0.55	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Scarlet Red	Coating	0.34	0.39	0.85	N	Y	No	10
Valspar Corporation	Fluropon	Shelburne	Coating	0.69	0.68	0.85	Y	Y	No	30
Valspar Corporation	Fluropon	Sierra Gold	Coating	0.47	0.46	0.86	N	Y	No	30
Valspar Corporation	Fluropon	Sierra Tan	Coating	0.35	0.34	0.86	N	Y	No	30
Valspar Corporation	Fluropon	Sierra Tan	Coating	0.38	0.38	0.86	N	Y	No	30
Valspar Corporation	Fluropon	Silver Gray	Coating	0.29	0.26	0.86	N	Y	No	30
Valspar Corporation	Fluropon	Silver Metal	Coating	0.55	0.53	0.79	N	Y	No	30
Valspar Corporation	Fluropon	Silver Metallic	Coating	0.59	0.60	0.80	N	Y	No	30
Valspar Corporation	Fluropon	Slate Gray	Coating	0.40	0.40	0.85	N	Y	No	30

Valspar Corporation	Fluropon	Snowdrift White	Coating	0.62	0.61	0.84	N	Y	No	30
Valspar Corporation	Fluropon	Spruce	Coating	0.28	0.29	0.86	N	Y	No	30
Valspar Corporation	Fluropon	Stone White	Coating	0.60	0.56	0.86	N	Y	No	30
Valspar Corporation	Fluropon	Surrey Beige	Coating	0.42	0.41	0.85	N	Y	No	30
Valspar Corporation	Fluropon	Taupe	Coating	0.30	0.29	0.85	N	Y		30
Valspar Corporation	Fluropon	Teal Patina	Coating	0.37	0.37	0.86	N	Y	No	30
Valspar Corporation	Fluropon	Terra Cotta	Coating	0.35	0.35	0.87	N	Y	No	30
Valspar Corporation	Fluropon	Tundra	Coating	0.34	0.34	0.85	N	Y	No	30
Valspar Corporation	Fluropon SR	Birch White	Coating	0.64	0.65	0.85	N	Y	No	30
Valspar Corporation	Fluropon SR	Cool Brite Red	Coating	0.44	0.43	0.84	N	Y	No	30
Valspar Corporation	Fluropon SR	Cool Copper Penny	Coating	0.44	0.41	0.81	N	Y	No	30
Valspar Corporation	Fluropon SR	Coronado Red	Coating	0.38	0.37	0.84	N	Y	No	30
Valspar Corporation	Fluropon SR	Desert Beige	Coating	0.35	0.34	0.86	N	Y	No	30
Valspar Corporation	Fluropon SR	Light Seawolf	Coating	0.39	0.40	0.86	N	Y	No	30
Valspar Corporation	Fluropon SR	Limestone	Coating	0.56	0.56	0.84	N	Y	No	30
Valspar Corporation	Fluropon SR	Moss	Coating	0.28	0.28	0.86	N	Y	No	30
Valspar Corporation	Fluropon SR	Polar White	Coating	0.65	0.64	0.86	Y	Y	No	30
Valspar Corporation	Fluropon SR	Regal Gray	Coating	0.44	0.44	0.84	N	Y	No	30
Valspar Corporation	Fluropon SR	Ruby Red	Coating	0.40	0.34	0.82	N	Y	No	30
Valspar Corporation	Fluropon SR	Sahara Tan	Coating	0.41	0.39	0.86	N	Y	No	30
Valspar Corporation	Fluropon SR	Sierra White	Coating	0.72	0.69	0.85	Y	Y	No	30
Valspar Corporation	Fluropon SR Classic II	Zinc	Coating	0.51	0.49	0.79	N	Y	No	30
Valspar Corporation	Fluropon SR Low Gloss	Colonial Red	Coating	0.35	0.32	0.86	N	Y	No	30
Valspar Corporation	Fluropon SR Low Gloss	Jade Green	Coating	0.29	0.29	0.85	N	Y	No	30
Valspar Corporation	Fluropon SR Low Gloss	Marine Green	Coating	0.35	0.35	0.85	N	Y	No	30
Valspar Corporation	Fluropon SR Low Gloss	Old Town Grey	Coating	0.26	0.26	0.86	N	Y	No	30
Valspar Corporation	Weather X	Alamo White	Coating	0.64	0.62	0.85	N	Y	No	20
Valspar Corporation	Weather X	Ash Gray	Coating	0.48	0.47	0.87	N	Y	No	20
Valspar Corporation	Weather X	Autumn Red	Coating	0.35	0.32	0.85	N	Y	No	20
Valspar Corporation	Weather X	Aztec Gold	Coating	0.53	0.53	0.86	N	Y	No	20
Valspar Corporation	Weather X	Brilliant White	Coating	0.71	0.68	0.85	Y	Y	No	20
Valspar Corporation	Weather X	Burgundy	Coating	0.26	0.27	0.84	N	Y	No	20
Valspar Corporation	Weather X	Colony Green	Coating	0.36	0.35	0.87	N	Y	No	20
Valspar Corporation	Weather X	Crimson Red	Coating	0.33	0.32	0.85	N	Y	No	20
Valspar Corporation	Weather X	Crimson Red	Coating	0.38	0.32	0.86	N	Y	No	10
Valspar Corporation	Weather X	Evergreen	Coating	0.28	0.22	0.84	N	Y	No	20
Valspar Corporation	Weather X	Gold	Coating	0.47	0.48	0.86	N	Y	No	20
Valspar Corporation	Weather X	Hawaiian Blue	Coating	0.25	0.20	0.86	N	Y	No	20
Valspar Corporation	Weather X	High Gloss White	Coating	0.71	0.72	0.85	Y	Y	No	20
Valspar Corporation	Weather X	Light Stone	Coating	0.50	0.50	0.87	N	Y	No	20
Valspar Corporation	Weather X	Pewter Gray	Coating	0.32	0.25	0.85	N	Y	No	20
Valspar Corporation	Weather X	Polar White	Coating	0.60	0.59	0.85	N	Y	No	20
Valspar Corporation	Weather X	Roman Blue	Coating	0.32	0.29	0.85	N	Y	No	20
Valspar Corporation	Weather X	Rustic Red	Coating	0.28	0.24	0.85	N	Y	No	20
Valspar Corporation	Weather X	Rustic Red	Coating	0.36	0.35	0.86	N	Y	No	20
Valspar Corporation	Weather X	Tan	Coating	0.41	0.37	0.86	N	Y	No	20
Valspar Corporation	WeatherX SR	Blue	Coating	0.25	0.25	0.86	N	Y	No	20
Valspar Corporation	WeatherX SR	Brite White	Coating	0.71	0.68	0.85	Y	Y	No	20
Valspar Corporation	WeatherX SR	Burgundy	Coating	0.26	0.27	0.84	N	Y	No	20
Valspar Corporation	WeatherX SR	Desert Sand	Coating	0.42	0.36	0.87	N	Y	No	20
Valspar Corporation	WeatherX SR	Ivory	Coating	0.66	0.65	0.85	Y	Y	No	20
Valspar Corporation	WeatherX SR	Pewter Gray	Coating	0.32	0.25	0.85	N	Y	No	20
Valspar Corporation	WeatherX SR	Red	Coating	0.28	0.24	0.85	N	Y	No	20
Valspar Corporation	WeatherX SR	Saddle Tan	Coating	0.48	0.47	0.87	N	Y	No	20
Valspar Corporation	WeatherX SR	Saddle Tan	Coating	0.48	0.47	0.87	N	Y	No	20
Valspar Corporation	WeatherX SR	Tan	Coating	0.41	0.37	0.86	N	Y	No	20
Valspar Corporation	WeatherX SR	Taupe	Coating	0.38	0.38	0.87	N	Y	No	20
Valspar Corporation	WeatherX SR	USDA White	Coating	0.61	0.64	0.85	N	Y	No	20
W.P. Hickman Systems, Inc.	W.P. Hickman	HK Aluminum Shield	Coating	0.69	0.53	0.40	Y	Y	No	5
W.P. Hickman Systems, Inc.	W.P. Hickman	Hickman Premium	Coating	0.83	0.71	0.89	Y	Y	No.	10
W.P. Hickman Systems, Inc.	W.P. Hickman	SOLARFLECT	Coating	0.89	0.88	0.89	Y	N	No	5-15
W.P. Hickman Systems, Inc.	W.P. Hickman	White Roof Coating	Coating	0.85	0.76	0.90	Y	N	No	5
W.P. Hickman Systems, Inc.	W.P. Hickman	White Roof Coating WC	Coating	0.77	0.55	0.89	Y	N		5
Water Tight Technologies	BRITE-n-EZ	Styrene/Acrylic Roof Coating	Coating	0.85	0.73	0.90	Y	N	No	15
Western Colloid S.C., Inc.	Western Colloid	ElastaHyde 720 ARC	Coating	0.84	0.75	0.89	Y	N	No	10
Western Colloid S.C., Inc.	Western Colloid	ElastaHyde 770 AXP	Coating	0.83	0.70	0.88	Y	N	No	10
Western Colloid S.C., Inc.	Western Colloid	ElastaHyde 790 AFC	Coating	0.84	0.71	0.90	Y	N	No	10